


974-EP

cited in the European Search  
Report of EP 02 79 2029.7  
Your Ref.: NSC-4 974-EP



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) EP 1 160 346 A1

(12) **EUROPEAN PATENT APPLICATION**  
published in accordance with Art. 158(3) EPC

(43) Date of publication:  
05.12.2001 Bulletin 2001/49

(51) Int Cl.7: **C22C 38/00**, **C22C 38/06**,  
**C22C 38/58**, **C21D 9/46**

(21) Application number: **99958479.0**

(86) International application number:  
**PCT/JP99/06774**

(22) Date of filing: **02.12.1999**

(87) International publication number:  
**WO 00/50658 (31.08.2000 Gazette 2000/35)**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**

(30) Priority: **22.02.1999 JP 4331999**  
**21.05.1999 JP 14142399**  
**30.07.1999 JP 21798799**

(72) Inventors:  
• **TAKADA, Yoshihisa**  
**Nippon Steel Corp. Yawata Works**  
**Kitakyushu City Fukuoka 804-8501 (JP)**  
• **SUEHIRO, Masayoshi**  
**Nippon Steel Corp. Yawata Works**  
**Kitakyushu City Fukuoka 804-8501 (JP)**


(71) Applicant: **NIPPON STEEL CORPORATION**  
**Tokyo 100-8071 (JP)**

(74) Representative: **VOSSIUS & PARTNER**  
**Siebertstrasse 4**  
**81675 München (DE)**

(54) **HIGH STRENGTH GALVANIZED STEEL PLATE EXCELLENT IN ADHESION OF PLATED  
METAL AND FORMABILITY IN PRESS WORKING AND HIGH STRENGTH ALLOY  
GALVANIZED STEEL PLATE AND METHOD FOR PRODUCTION THEREOF**

(57) The invention relates to a high strength hot-dip galvanized and galvanized steel sheets with excellent drawability for press forming and excellent plating adhesion that is useful as a member for automobiles, construction; electric devices and the like, and to a process for its manufacture. According to an embodiment of the invention, the steel sheet contains in terms of weight percent, C: 0.05-0.2%, Si: 0.2-2.0%, Mn: 0.2-2.5%, Al: 0.01-1.5%, Ni: 0.2-5.0%, P: <0.03% and S: <0.02%, the relationship between Si and Al being such that  $0.4(\%) \leq \text{Si} + 0.8 \text{ Al}(\%) \leq 2.0\%$  and the remainder consisting of Fe and unavoidable impurities, the volume percentage of the retained austenite is 2-20% and the steel sheet surface wherein the relationship between the Ni and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn plating layer comprising Al:  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

Fig.1



EP 1 160 346 A1

**BEST AVAILABLE COPY**

**Description**Technical Field

5 **[0001]** The present invention relates to a high strength steel sheet that is useful as a member for automobiles, construction, electric devices and the like and to a process for its manufacture, and more particularly it relates to a high strength hot-dip galvanized steel sheet with excellent draw ability properties for press forming and excellent plating adhesion, to a hot-dip galvanized plated steel sheet, and to a process for its manufacture.

Background Art

10 **[0002]** A current area of research on members such as cross members and side members of automobiles and the like is directed toward achieving lighter weight for the purpose of realizing lower fuel consumption and, in the area of materials, progress is being made in achieving higher strength in a manner that guarantees strength while producing thinner products. However, since the press formability of most materials is inferior with increasing strength, achieving such lighter weight members requires the development of steel sheets that exhibit both satisfactory press formability and high strength properties. The index values for formability include the elongation as well as the n value and r value obtained in tensile testing, and in the current situation, where one of the targets is to simplify the pressing steps through greater integration, it is important for the n value to be large, thus corresponding to uniform elongation.

15 **[0003]** For this purpose, there have been developed hot rolled steel sheets and cold rolled steel sheets that take advantage of the transformation-induced plasticity of the retained austenite in steel. These are steel sheets consisting of about 0.07-0.4% C, about 0.3-2.0% Si and about 0.2-2.5% Mn as the basic alloy elements, without any expensive alloy elements, and containing retained austenite in the microstructure by heat treatment characterized by accomplishing bainite transformation at an inner and outer temperature of 300-450°C after annealing in the two-phase region; such steel sheets are disclosed, for example, in Japanese Unexamined Patent Publication No. 1-230715 and No. 2-217425. Such steel sheets are disclosed not only as cold rolled steel sheets manufactured by continuous annealing, but also as hot rolled steel sheets obtained by controlling the cooling and coiling temperature with a runout table, as in Japanese Unexamined Patent Publication No. 1-79345, for example.

20 **[0004]** The plating of automobile members is advancing for the purpose of improving corrosion resistance and outer appearance to reflect higher quality in automobiles, and at the current time galvanized or galvanized steel sheets are used for most members other than special internally-mounted members. From the standpoint of corrosion resistance, therefore, it is effective to coat such steel sheets with Zn or Fe-Zn, however, since high strength steel with a high Si content also has an oxidation film on the steel sheet surface, it presents a problem in that minute unplated regions result upon hot-dip galvanizing, and in that the plating adhesion of worked regions after alloying is inferior; at the current time, however, it has not been possible to realize galvanized steel sheets with excellent plating adhesion at worked regions, excellent corrosion resistance and high strength and high ductility.

25 **[0005]** For example, since the steel sheets disclosed in Japanese Unexamined Patent Publication No. 1-230715 or No. 2-217425 contain 0.3-2.0% added Si and take advantage of its unique bainite transformation to guarantee retained austenite, unless rather strict control is kept on the cooling after annealing in the two-phase temperature range, and the holding at an internal temperature of 300-450°C, it is impossible to obtain the intended microstructure and the resulting strength and elongation are outside of the target ranges. While such a thermal history can be realized industrially with continuous annealing equipment and during the cooling step with the runout table after hot rolling, the austenite transformation is completed rapidly at 450-600°C and therefore control is required for a particularly short holding time at 450-600°C. Even at 350-450°C, the microstructure varies considerably depending on the holding time, and any shift from the desired conditions results in only a low level of strength and elongation. For hot-dip galvanizing the holding time at 450-600°C is usually long, and therefore this technique cannot be applied. Furthermore, there is a problem in that the inclusion of Si as the alloy element results in poorer plating, and this impedes passage through the hot-dip galvanizing equipment to make a plated steel sheet.

30 **[0006]** In order to solve these problems, there have been disclosed steel sheets with improved plating properties through restriction of the Si concentration, for example, in Japanese Unexamined Patent Publication No. 5-247586 and Japanese Unexamined Patent Publication No. 6-145788. According to such processes, Al is added instead of Si to produce retained austenite. However, since Al like Si is also more easily oxidized than Fe, the Al and Si tend to concentrate on the steel sheet surface as an oxidized film, making it impossible to achieve adequate plating adhesion. Another process disclosed in Japanese Unexamined Patent Publication No. 5-70886 adds Ni to improve the plating wettability. For this process, however, it is not disclosed what relationship between the Si or Al and Ni is necessary to inhibit the plating wettability.

35 **[0007]** Furthermore, Japanese Unexamined Patent Publication No. 4-333552 and No. 4-346644 disclose processes whereby rapid low temperature heating is conducted after Ni preplating for alloying treatment after hot-dip Zn plating,

as processes for hot-dip galvannealing of high Si high strength steel sheets. However, since these processes require Ni pre-plating, the problem of requiring new equipment arises. These processes also do not allow retention of retained austenite in the final microstructure, nor is any such mention made for this process.

[0008] The present invention solves the aforementioned problems and represents the discovery of the features of the composition and microstructure of a high strength steel sheet with improved surface corrosion resistance and excellent plating adhesion allowing its manufacture with hot-dip galvanizing equipment, as well as satisfactory press formability.

#### Disclosure of the Invention

[0009] It is an object of the present invention to provide a high strength hot-dip galvannealed steel sheet with satisfactory press formability and plating adhesion and a process for efficient manufacture of the steel sheet.

[0010] The present inventors have carried out diligent research on plating properties and steel sheet components in order to provide a high strength hot-dip galvannealed steel sheet and a process for its manufacture, and have completed the present invention by concentrating on the steel sheet surface layer, to arrive at the gist of the invention as described below.

(1) A high strength hot-dip galvannealed steel sheet with excellent plating adhesion and press formability, the steel sheet containing, in terms of weight percent,

C: 0.05-0.2%,  
Si: 0.2-2.0%,  
Mn: 0.2-2.5%,  
Al: 0.01-1.5%,  
Ni: 0.2-5.0%,  
P: <0.03% and  
S: <0.02%

where the relationship between Si and Al is such that  $0.4(\%) \leq \text{Si} + 0.8 \text{ Al}(\%) \leq 2.0\%$  and the remainder consists of Fe and unavoidable impurities, characterized in that the volume percentage of the retained austenite in the steel sheet is 2-20%, and the steel sheet surface wherein the relationship between the Ni and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$  has a Zn plating layer comprising Al:  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

(2) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized by also containing, in addition to the steel sheet components mentioned in (1) above, in terms of weight percent, Cu at less than 2.0%, wherein the volume percentage of the retained austenite in the steel sheet is 2-20%, and the relationship between the Ni, Cu and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ .

(3) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized by also containing, in addition to the steel sheet components mentioned in (2) above in terms of weight percent, B at 0.0002-0.01%, wherein the relationship of Cu and B is such that  $\text{B} \times \text{Cu}(\%) \geq 0.00005(\%)$ .

(4) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized by also containing, in addition to the steel sheet components mentioned in any of (1) to (3) above in terms of weight percent, at least one from among Co at <0.3% and Sn at <0.3%, wherein the volume percentage of the retained austenite in the steel sheet is 2-20% and the relationship between the Ni, Cu, Co, Sn and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu} + \text{Co} + \text{Sn}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ .

(5) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized by also containing, in addition to the steel sheet components mentioned in any of (1) to (4) above in terms of weight percent, at least one from among Mo: <0.5%, Cr: <1%, V: <0.3%, Ti: <0.06%, Nb: <0.06%, REM: <0.05%, Ca: <0.05%, Zr: <0.05%, Mg: <0.05%, Zn: <0.02%, W: <0.05%, As: <0.02%, N: <0.03% and O: <0.05%.

(6) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized in that the steel sheet surface of any of (1) to (5) above has a Zn plating layer containing at least one from among Al:  $\leq 1\%$ , Mn: <0.02%, Pb: <0.01%, Fe: <0.2%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with the remainder Zn and unavoidable impurities.

(7) A high strength hot-dip galvannealed steel sheet with excellent press formability, characterized in that a steel sheet containing in terms of weight percent,

C: 0.05-0.2%,

Si: 0.2-2.0%,  
 Mn: 0.2-2.5%,  
 Al: 0.01-1.5%,  
 Ni: 0.2-5.0%,  
 P: <0.03% and  
 S: <0.02%,

where the relationship between Si and Al is such that  $0.4(\%) \leq \text{Si} + 0.8 \text{ Al}(\%) \leq 2.0\%$ , the remainder consists of Fe and unavoidable impurities, the volume percentage of the retained austenite in the steel sheet is 2-20% and the relationship between the Ni and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe: 8-15%, Al:  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

(8) A high strength hot-dip galvanized steel sheet with excellent press formability, characterized in that a steel sheet also containing, in addition to the steel sheet components mentioned in (6) above in terms of weight percent, Cu at less than 2.0% with the remainder Fe and unavoidable impurities, wherein the volume percentage of the retained austenite in the steel sheet is 2-20% and the relationship between the Ni, Cu and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

(9) A high strength hot-dip galvanized steel sheet with excellent press formability, characterized in that a steel sheet also containing, in addition to the steel sheet components mentioned in (7) above in terms of weight percent, B at 0.0002-0.01% where the relationship between Cu and B is such that  $\text{B} \times \text{Cu}(\%) \geq 0.00005(\%)$  with the remainder Fe and unavoidable impurities, has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

(10) A high strength hot-dip galvanized steel sheet with excellent press formability, characterized in that a steel sheet also containing, in addition to the steel sheet components mentioned in any of (7) to (9) above in terms of weight percent, at least one from among Co at <0.3% and Sn at  $\leq 0.3\%$  with the remainder Fe and unavoidable impurities, wherein the volume percentage of the retained austenite in the steel sheet is 2-20% and the relationship between the Ni, Cu, Co, Sn and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu} + \text{Co} + \text{Sn}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

(11) A high strength hot-dip galvanized steel sheet with excellent press formability, characterized by also containing, in addition to the steel sheet components mentioned in any of (7) to (10) above in terms of weight percent, at least one from among Mo: <0.5%, Cr: <1%, V: <0.3%, Ti: <0.06%, Nb: <0.06%, REM: <0.05%, Ca: <0.05%, Zr: <0.05%, Mg: <0.05%, Zn: <0.02%, W: <0.05%, As: <0.02%, N: <0.03% and O: <0.05%.

(12) A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, characterized in that the steel sheet surface of any of (7) to (11) above has a Zn plating layer containing at least one from among Fe: 8-15%, Al:  $\leq 1\%$ , Mn: <0.02%, Pb: <0.01%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with the remainder Zn and unavoidable impurities.

(13) A process for manufacture of a high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability characterized by having 2-20% retained austenite and a Zn plating layer comprising Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities, whereby a steel sheet having the components of any one of (1) to (6) above is cast and solidified and then heated at 1150° or higher for at least 45 minutes, after which it is subjected to hot rolling and coiling at 400-780°C, and then after descaling treatment is subjected to cold rolling at a 35-85% draft, subsequently annealed from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C, and finally cooled to 350-500°C at a cooling rate of 2-200 °C/s, subjected to hot-dip zinc plating and then cooled to below 250°C at a cooling rate of at least 5 °C/s.

(14) A process for manufacture of a high strength hot-dip galvanized steel sheet with excellent press formability characterized by having 2-20% retained austenite and a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities, whereby a steel sheet having the components of any one of (7) to (12) above is cast and solidified and then heated at 1150° or higher for at least 45 minutes, after which it is subjected to hot rolling and coiling at 400-780°C, and then after descaling treatment is subjected to cold rolling at a reduction ratio of 35-85%, subsequently annealed from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C, and finally cooled to 350-500 °C at a cooling rate of 2-200 °C/s, subjected to hot-dip galvanizing and held in a temperature range of 450-600 °C for 5 seconds to 1 minute prior to cooling to below 250°C at a cooling rate of at least 5 °C/s.

(15) A process for manufacture of a high strength hot-dip galvanized steel sheet with excellent press formability according to (13) or (14) above, characterized in that the cold-rolling is followed by annealing from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C and then by cooling to 350-500°C at a cooling rate

of 2-200 °C/s and held in that temperature range for no more than 5 minutes.

#### Best Mode for Carrying Out the Invention

**[0011]** The reason for the limits to the components of the present invention is to provide a high strength hot-dip galvanized steel sheet with satisfactory press formability and plating adhesion, and this will now be explained in detail.

**[0012]** C is an austenite-stabilizing element, and it migrates from ferrite to austenite in the two-phase temperature range and the bainite transformation temperature range. As a result, the chemically stabilized austenite remains at 2-20% even after cooling to room temperature, giving satisfactory formability by transformation-induced plasticity. If C is present at less than 0.05% it is difficult to guarantee retained austenite of at least 2%, and the desired object cannot be achieved. The C concentration must not exceed 0.2% in order to avoid poor weldability.

**[0013]** Si does not dissolve in cementite and therefore delays the transformation from austenite to cementite at 350-600°C because its controlling process is the diffusion of Si which is very slow at the temperature. The chemical stability of austenite increases during this time because of accelerated C concentration in the austenite, causing transformation-induced plasticity and making it possible to guarantee retained austenite to contribute to satisfactory formability. If the amount of Si is less than 0.2% this effect cannot be achieved. On the other hand, it must be no greater than 2.0% because, if the Si concentration is any higher, the plating properties are impaired.

**[0014]** Mn is an austenite-stabilizing element, and since it retards decomposition of austenite to perlite during the cooling to 350-600°C after annealing in the two-phase temperature range, it promotes inclusion of retained austenite in the microstructure during surface cooling to room temperature. If added at less than 0.2% it becomes necessary to increase the cooling rate to a level at which industrial control is no longer possible in order to inhibit decomposition to perlite, and such a situation is unacceptable. On the other hand, it is preferably not greater than 2.5% because the band structure will become more notable and impair the properties, while the spot welded sections will tend to fracture within nuggets.

**[0015]** Al is used as a deoxidizing material because, like Si, it does not dissolve in cementite and therefore delays the ongoing transformation by inhibiting precipitation of cementite when held at 350-600°C. However, since its ferrite-forming ability is stronger than Si and it therefore accelerates transformation to ferrite, so that C is concentrated in the austenite from the moment of annealing in the two-phase temperature range even for a very short time, thus increasing the chemical stability, only a trace amount of formability-impairing martensite is present in the microstructure after cooling to room temperature. When copresent with Si, therefore, little change occurs in the strength or elongation depending on the holding conditions at 350-600°C, and it is therefore easy to achieve satisfactory press formability with high strength. The Al must therefore be added to at least 0.01%. Together with Si, "Si + 0.8Al" must be at least 0.4%. On the other hand, as is the case with Si, the Al concentration must not exceed 1.5% to avoid impairing the plating adhesion. In order to guarantee plating adhesion together with Si, "Si + 0.8Al" must be no greater than 2.0%.

**[0016]** Ni is the most important element according to the invention, and like Mn it is an austenite-stabilizing element and it also improves the strength and plating adhesion. In addition, like Si and Al, Ni also does not dissolve in cementite and therefore delays the ongoing transformation by inhibiting precipitation of cementite when held at 350-600°C. In a steel sheet containing Si or Al, when producing a plated steel sheet in a continuous hot-dip galvanizing line, Si and Al are more easily oxidized than Fe and are thus concentrated on the steel sheet surface, forming Si or Al oxides and reducing the plating adhesion. The inventors therefore attempted to prevent this reduction in plating adhesion despite the surface concentration of Si or Al, by allowing Ni to concentrate on the surface instead since it is more resistant to oxidation than Fe. By experimentation it was determined that a 0.5 µm section of the steel sheet surface reacts with the Zn layer during the plating reaction. In order to improve the plating adhesion, therefore, it is sufficient to control the surface concentrated layer of a 0.5 µm section of the steel sheet surface. If the Ni is present at 0.2% or less, it is not possible to achieve satisfactory plating adhesion with steel according to the invention. If the Ni concentration is 5% or higher the retained austenite exceeds 20% such that the elongation falls below the range of the invention. As a result of experimentation it has been found that satisfactory plating adhesion can only be obtained if the Ni concentration, together with Si and Al in 0.5 µm of the steel sheet surface, is at least such that "Ni(%) ≥ 1/4 Si + 1/3 Al(%)" . This is illustrated in Fig. 1.

**[0017]** P is an element unavoidably included in steel as an impurity, and like Si, Al and Ni it does not dissolve in cementite and therefore delays the ongoing transformation by inhibiting precipitation of cementite when held at 350-600°C. However, since a P concentration exceeding 0.03% notably impairs the ductility of the steel sheet while also undesirably tending to result in fracture of spot welded sections within nuggets, the P concentration is limited to less than 0.03% according to the invention.

**[0018]** S, like P, is also an element unavoidably included in steel. A high S concentration may result in MnS precipitation leading to lower ductility while also undesirably tending to result in fracture of spot welded sections within nuggets, and therefore the S concentration is less than 0.02% according to the invention.

[0019] Cu, which, like Ni, is more resistant to oxidation than Fe, is an austenite-stabilizing element like Ni and Mn that also improves the strength and plating adhesion. Satisfactory plating adhesion can be achieved if the Ni and Cu concentration in 0.5  $\mu\text{m}$  of the steel sheet surface layer, together with Si and Al, is such that " $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ ". A Cu concentration of 2.0% or higher may produce Cu precipitates, thus impairing the material quality and  
 5 impeding the object of the invention. From the standpoint of preventing heat fracture by Cu when Cu is added, the relationship is preferably " $\text{Cu}(\%) < 3 \times \text{Ni}(\%)$ ".

[0020] B is copresent with Cu and lowers the transformation point to inhibit precipitation of cementite and increase the volume percentage of retained austenite by delaying the progress of transformation. An adequate effect cannot be achieved if the B concentration is 0.0002% or lower. The upper limit for B is specified based on the concentration at  
 10 which economy is affected, and this upper limit is set to 0.01%. In order to exhibit the effect of B and Cu together, B and Cu must be in a relationship that satisfies the inequality  $\text{B} \times \text{Cu}(\%) \geq 0.00005(\%)$ . To exhibit a more powerful effect, the relationship is preferably  $\text{B} \times \text{Cu}(\%) \geq 0.00008(\%)$ .

[0021] The plating adhesion can also be improved by further adding another species similar to Ni and Cu that is more resistant to oxidation than Fe, such as Sn or Co. Satisfactory plating adhesion can be achieved if the Ni, Cu, Sn and Co concentration in 0.5  $\mu\text{m}$  of the steel sheet surface, together with Si and Al, is at least such that " $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ ". A higher Sn concentration results in Sn-based heat fracture, and it is therefore limited to less than  
 15 0.3%. Co is an expensive metal and its upper limit is therefore 0.3%.

[0022] Mo, Cr, V, Ti, Nb, B, W, O, Zn and As are elements that increase the strength, while REM, Ca, Zr and Mg are elements that guarantee satisfactory elongation by combining with S to reduce inclusions, and N is an austenite-stabilizing element; the addition, as necessary, of one or more from among Mo: <0.5%, Cr: <1%, V: <0.3%, Ti: <0.06%, Nb: <0.06%, B: <0.01%, REM: <0.05%, Ca: <0.05%, Zr: <0.05%, Mg: <0.05%, Zn: <0.02%, W: <0.05%, As: <0.02%, N: <0.03% and O: <0.05% will not interfere with the gist of the invention. The effects of these elements are saturated  
 20 beyond the upper limits given above, and therefore any further addition simply increases the cost.

[0023] The steel sheet of the invention comprises the basic components described above, but the gist of the invention is not hampered even if other elements are included in addition to these and Fe, such as Ta, Te, Be, Ru, Os, Rh, Ir, Pd, Pt, Ag, Au, Cd, Hg, Ge, Pb, Sb, Bi, Se and Te which are commonly included unavoidably in steel, and these  
 25 elements may be added at up to 0.01% in total.

[0024] The ductility of the steel sheet of the invention as a final product is determined by the volume percentage of retained austenite in the product. Although the retained austenite in the microstructure is stably present in the absence of deformation, applied deformation transforms it into martensite resulting in transform-induced plasticity, thus giving  
 30 satisfactory formability with high strength. If the volume percentage of retained austenite is less than 2% the effect will not be clearly recognizable. On the other hand, if the volume percentage of retained austenite is over 20%, a large amount of martensite may be present in the press forming state in cases of extremely severe shaping, which may cause problems in terms of secondary workability or impact resistance; according to the invention, therefore, the volume  
 35 percentage of retained austenite is no greater than 20%. The structure also includes ferrite, bainite, martensite and carbides.

[0025] According to the invention, the steel sheet has a Zn plating layer or a Zn alloy plating layer, which will now be explained.

[0026] The Zn plating layer includes Al:  $\leq 1\%$  as well as, depending on the case, at least one from among Mn: <0.02%, Pb: <0.01%, Fe: <0.2%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with  
 40 the remainder Zn and unavoidable impurities. The Al content of the plating is limited to no greater than 1% because if the Al content exceeds 1% the segregated Al will form a local battery in the plating, thus impairing the corrosion resistance. If Mn, Pb, Fe, Sb, Ni, Cu, Sn, Co, Cd and Cr are present in high amounts the edge corrosion resistance is impaired, and these are therefore limited to Mn: <0.02%, Pb: <0.01%, Fe: <0.2%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%,  
 45 Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%.

[0027] The Zn alloy plating layer includes Fe: 8-15%, Al:  $\leq 1\%$  as well as, depending on the case, at least one from among Mn: <0.02%, Pb: <0.01%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with the remainder Zn and unavoidable impurities. The Fe content of the plating is limited to at least 8%  
 50 because at less than 8% the chemical treatment (phosphate treatment) properties and coating adhesion are poorer. Also, the Fe content is limited to no greater than 15% because overalloying occurs at greater than 15%, and the plating adhesion of the worked sections is poorer. The Al content of the plating is limited to no greater than 1% because when the Al content exceeds 1% the segregated Al will form a local battery in the plating, thus impairing the corrosion resistance. If Mn, Pb, Sb, Ni, Cu, Sn, Co, Cd and Cr are present in high amounts the edge corrosion resistance is impaired, and these are therefore limited to Mn: <0.02%, Pb: <0.01%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%,  
 55 Cd: <0.01% and Cr: <0.05%.

[0028] The Zn plating layer and Zn alloy plating layer of the invention are as described above, but they may also contain other impurities.

[0029] Furthermore, while no particular restrictions are placed on the Zn alloy plating layer thickness, from the stand-

point of corrosion resistance it is preferably at least 0.1  $\mu\text{m}$  and from the standpoint of workability it is preferably no thicker than 15  $\mu\text{m}$ .

[0030] The hot-dip galvanized steel sheet of the invention and a process for manufacture of a hot-dip galvanized steel sheet of the invention will now be explained.

[0031] The hot-dip galvanized steel sheet of the invention may be obtained by casting and solidifying a steel sheet satisfying the conditions for the component composition as explained above and then heating it at 1150°C or higher for at least 45 minutes, subjecting it to hot rolling and coiling at 400-780°C, and then after descaling treatment, subjecting it to cold rolling at a reduction ratio of 35-85%, subsequently annealing it from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C, cooling it to 350-500°C at a cooling rate of 2-200 °C/s, further holding it for up to 5 minutes in that temperature range depending on the case, and finally subjecting it to hot-dip galvanizing and cooling to below 250°C at a cooling rate of at least 5 °C/s.

[0032] A hot-dip galvanized steel sheet of the invention may be obtained by casting and solidifying a steel sheet satisfying the conditions for the component composition as explained above and then heating it at 1150°C or higher for at least 45 minutes, subjecting it to hot rolling and coiling at 400-780°C, and then after descaling treatment, subjecting it to cold rolling at a reduction ratio of 35-85%, subsequently annealing from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C, cooling it to 350-500°C at a cooling rate of 2-200 °C/s, further holding it for up to 5 minutes in that temperature range depending on the case, and finally subjecting it to hot-dip galvanizing and further holding it from 5 seconds to 1 minute in a temperature range of 450-600°C prior to cooling to below 250°C at a cooling rate of at least 5 °C/s.

[0033] The reasons for each of these manufacturing conditions will now be explained.

[0034] The holding temperature and holding time after casting and solidification are important to increase the Ni concentration of the steel sheet surface layer section prior to plating. Because Ni is more resistant to oxidation than Fe, Ni is not incorporated in the oxidation scales produced during heating, and therefore concentrates in the steel sheet surface layer. The concentrated Ni remains even after cold rolling, thus improving the plating properties. For the relationship between Ni, Si and Al in a 0.5  $\mu\text{m}$  steel sheet surface layer to satisfy  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , it is necessary for the heating temperature to be at least 1150°C and the holding time at 1150°C or higher to be at least 45 minutes.

[0035] The coiling temperature after hot rolling is also important to increase the Ni concentration of the steel sheet surface layer section prior to plating. Ni also fails to be incorporated in the oxidation scales produced after coiling, thus concentrating in the steel sheet surface layer and improving the plating properties. When steel such as a steel according to the invention is coiled at low temperature, the Ni concentration is insufficient leading to problems with the Zn plating adhesion, while hardening results at burnt sections, thus complicating the subsequent scale removal by acid washing, etc. and the cold rolling. Conversely, when coiling is carried out at high temperature the Zn plating property is improved and the cementite becomes coarser and softer thus facilitating acid washing and cold rolling, but too much time is then required for renewed dissolution of the cementite during annealing, such that sufficient austenite is not retained. Consequently, it was determined that the coiling after hot rolling must be carried out at 400-780°C to avoid such inconveniences. However, since it is desirable for the acid washing and cold rolling of hot-rolled steel sheets to be as easy as possible, the coiling temperature is preferably 550-750°C.

[0036] The hot rolling is followed by descaling, but there are no particular restrictions on the descaling method.

[0037] If the cold rolling reduction ratio is less than 35% the structure will not be sufficiently fine and the ductility will therefore be inferior due to insufficient retained austenite in the subsequent annealing step. On the other hand, if the reduction ratio is greater than 85% there will be too great a load on the rolling machine, and therefore the optimum reduction ratio during cold rolling was determined to be 35-85%.

[0038] In continuous annealing of the cold rolled steel sheet after cold rolling, heating is first performed in a temperature range from the Ac1 transformation point to the Ac3 transformation point to make a two-phase microstructure [ferrite + austenite]. If the heating temperature at this time is below 650°C, too much time will be required for renewed dissolution of the cementite and only a small amount of austenite will be present, and therefore the lower limit for the heating temperature is 650°C. If the heating temperature is too high the volume percentage of austenite becomes too large and the C concentration of the austenite is reduced, and therefore the upper limit for the heat temperature is 900°C. If the holding time is too short there will tend to be more non-dissolved carbides present, and the amount of austenite will be reduced. If the holding time is lengthened the crystal grains will have a greater tendency to become coarse, resulting in a poorer strength/ductility balance. According to the invention, therefore, the holding time is set to be from 10 seconds to 6 minutes.

[0039] After holding at annealing temperature, steel sheets are cooled to 350-500°C, at a cooling rate of 2-200 °C/s. This is for the purpose of bringing the austenite produced by heating in the two-phase range directly to the bainite transformation range without transformation to perlite, so that, by subsequent treatment, the desired microstructure and properties are obtained. If the cooling rate at this time is less than 2 °C/s, most of the austenite will transform to perlite during cooling, so that the amount of retained austenite cannot be guaranteed. If the cooling rate is greater than 200 °C/s, the cooling end point temperature will vary largely in the widthwise direction and lengthwise direction, making

it impossible to manufacture a uniform steel sheet.

[0040] This may be followed by holding at up to 5 minutes in a range of 350-500°C, depending on the case. Holding at this temperature prior to Zn plating accelerates bainite transformation and allows stabilization of retained austenite with concentrated C, to allow more stable manufacture of a steel sheet with both strength and elongation. If the cooling end point temperature from the two-phase range is a temperature higher than 500°C, the subsequent temperature holding will result in decomposition of austenite to carbides, such that no austenite can be retained. If the cooling end point temperature is below 350°C, the greater part of the austenite transforms to martensite and, therefore, despite higher strength the press formability is inferior while the steel sheet temperature must be increased during Zn plating thus requiring application of greater heat energy and creating an inefficient situation. If the holding time exceeds 5 minutes both the strength and press formability are inferior due to precipitation of carbides and loss of untransformed austenite by heating after Zn plating, and therefore the holding temperature is limited to no longer than 5 minutes.

[0041] For manufacture of a hot-dip galvanized steel sheet, the plating is followed by cooling to below 250°C at a cooling rate of 5 °C/s or greater. This accelerates bainite transformation during Zn plating, producing a microstructure comprising a combination of virtually carbide-free bainite and retained austenite in which C that has been swept out from those sections has been concentrated and the Ms point has fallen to below room temperature, and ferrite that is purified during the two-phase range heating; the result is both high strength and formability. Consequently, if the cooling rate after holding is slower than 5°C or the cooling end point temperature is higher than 250°C, the austenite with concentrated C after cooling will also precipitate carbide and decompose to bainite, such that the desired object cannot be achieved due to a reduced amount of retained austenite for improvement of the workability by transformation induced plasticity. In order to leave a greater amount of retained austenite, a holding time of less than 5 minutes in a temperature range of 350-400°C after hot-dip zinc plating is preferred.

[0042] For manufacture of a hot-dip galvanized steel sheet, the hot-dip galvanizing is followed by holding from 5 seconds to 1 minute in a temperature range of 450-600°C, and then by cooling to below 250°C at a cooling rate of at least 5 °C/s. This is for the alloying reaction between Fe and Zn, and also for structural considerations. With steel according to the invention, which also contains Si or Al, it is possible to utilize the fact that transformation from austenite to bainite is separated in two stages, to realize a structure comprising a combination of virtually carbide-free bainite and retained austenite in which C that has been swept out from those sections has been concentrated and the Ms point has fallen to below room temperature, as well as ferrite that is purified during the biphasic range heating, whereby both high strength and formability are achieved. If the holding temperature exceeds 600°C, perlite is produced and retained austenite is therefore absent, while the alloying reaction proceeds leading to excessive an Fe concentration of greater than 15% in the plating. On the other hand, if the heating temperature is below 450°C the alloying reaction rate of the plating is slowed, so that the Fe concentration of the plating is lower. Also, with a holding time of less than 5 seconds the bainite production is insufficient and the C concentration in the non-transformed austenite is also insufficient, such that martensite is produced during cooling thus impairing the formability, while the alloying reaction of the plating is also inadequate. If the holding time is longer than one minute, the plating becomes overalloyed, thus tending to result in peeling of the plating during shaping. If the cooling rate after holding is slower than 5°C, the bainite transformation will proceed when the cooling end point temperature is above 250°C, and even the austenite with concentrated C due to the previous reaction will precipitate carbide and decompose to bainite, so that the desired object cannot be achieved due to a reduced amount of retained austenite for improvement of the workability by transformation induced plasticity.

[0043] The hot-dip galvanizing temperature is preferably between the melting temperature of the plating bath and 500°C. If it is above 500°C the vapor from the plating bath becomes excessive to the point of hampering manageability. While there is no need for particular restrictions on the heating rate to the holding temperature after plating, from the standpoint of the plating structure and steel microstructure it is preferably 3 °C/s.

[0044] The heating temperatures and cooling temperatures for each step described above do not need to be constant so long as they are within the specified ranges, and with variation within those ranges there is no deterioration, and there is often improvement, in the properties of the final product.

[0045] For further improvement in the plating adhesion, a simple or composite plating of Ni, Cu, Co or Fe may be provided on the steel sheet prior to the plating annealing after cold rolling. For still further improvement in the plating adhesion, the atmosphere during the steel sheet annealing may be adjusted so that the steel sheet surface is oxidized first and then reduced for purification of the steel sheet surface before plating. There is also no problem with further improving the plating adhesion by acid washing or polishing before annealing to remove oxides from the steel sheet surface. Such treatment can greatly enhance the plating adhesion.

## Examples

[0046] Steel comprising the components listed in Table 1 was hot rolled, cold rolled, annealed and plated under the conditions shown in Table 2, and then subjected to tempered rolling at 0.6% to manufacture steel sheets. The manu-



factured steel sheets were subjected to the "tensile test", "retained austenite measurement test", "welding test", "0.5  $\mu\text{m}$  steel sheet surface layer section analysis", "plating property", "plating adhesion" and "plating layer concentration measurement", as explained below.

[0047] The "tensile test" was an ordinary temperature tensile test conducted on a JIS #5 tensile test strip, with a gauge thickness of 50 mm and a pull rate of 10 mm/min.

[0048] The "retained austenite measurement test" was measurement by the so-called "5-peak" method whereby a 1/4 inner layer of the sheet thickness from the surface layer is chemically polished and the  $\alpha$ -Fe and  $\gamma$ -Fe intensity are determined by X-ray analysis using an Mo tube.

[0049] The "welding test" was carried out by spot welding under the conditions, welding current: 10 kA, applied pressure: 220 kg, welding time: 12 cycles, electrode diameter: 6 mm, electrode shape: domed, tip 6 $\Phi$ -40R, and the number of continuous spots until the point at which the nugget diameter fell below 4 t (t: sheet thickness) was evaluated. The evaluation scale was the following.  $\bigcirc$ : >1000 continuous spots,  $\Delta$ : 500-1000 continuous spots,  $\cdot$ : <500 continuous spots. Here,  $\bigcirc$  was defined as acceptable and  $\Delta/\cdot$  as unacceptable.

[0050] The "0.5  $\mu\text{m}$  steel sheet surface layer section analysis" was based on two types, measurement by EPMA analysis of a 0.5  $\mu\text{m}$  steel sheet section at the plating/sheet interface of a cross-section of the plated steel sheet, and EDS analysis by TEM observation of a sample prepared by the FIB method. For the measurement, a standard sample was used to construct a calibration curve. There was practically no difference between the measurements.

[0051] The "plating property" was determined by visually judging the condition of any non-plated sections on the outside of the plated steel sheet, and was evaluated based on the following scale.  $\odot$   $\leq 3$  /dm<sup>2</sup>,  $\bigcirc$ : 4-10 /dm<sup>2</sup>,  $\Delta$ : 11-15 /dm<sup>2</sup>,  $\cdot$   $\geq 16$  /dm<sup>2</sup>. Here,  $\odot$  / $\bigcirc$  were defined as acceptable and  $\Delta/\cdot$  as unacceptable.

[0052] The "plating adhesion" was determined by subjecting the plated steel sheet to a tape test after a 60° V bend test, and was evaluated based on the following scale.

Tape test blackening (%)

Evaluation:  $\odot$  ... 0 - <10

Evaluation:  $\bigcirc$  ... 10 - <20

Evaluation:  $\Delta$  ... 20 - <30

Evaluation:  $\cdot$  ...  $\geq 30$

( $\odot$  / $\bigcirc$  = acceptable,  $\Delta/\cdot$  = unacceptable)

[0053] The "plating layer concentration measurement" was conducted by ICP emission analysis after dissolving the plating layer in 5% hydrochloric acid containing an amine-based inhibitor.

[0054] The results of the performance evaluation tests are shown in Tables 3 and 4. Samples 1-32 of the invention were hot-dip galvanized steel sheets and hot-dip galvanized steel sheets with 2-20% retained austenite, total elongation of at least 30% even at 550 MPa or greater, and both satisfactory high strength and press formability, with satisfactory plating properties and weldability as well. In contrast, samples 33 and 34 had low C concentrations, samples 35 and 36 had high C concentrations, samples 37 and 38 had low Si concentrations, samples 39 and 40 had high Si concentrations, samples 41 and 42 had low Al concentrations, samples 43 and 44 had high Al concentrations, samples 45 and 46 failed to satisfy the relationship between Si and Al in the steel, samples 47 and 48 failed to satisfy the relationship for the concentrations in 0.5  $\mu\text{m}$  of the steel sheet surface, samples 49 and 50 had low Mn concentrations, samples 51 and 52 had high Mn concentrations, samples 53 and 54 had high P concentrations, samples 55 and 56 had high S concentrations, samples 57 and 58 had low Ni concentrations, samples 59 and 60 had high Ni concentrations, samples 61 and 62 had high Cu concentrations and samples 63 and 64 had high Al concentrations in the platings; these failed to satisfy the retained austenite amount, combination of high strength and press formability, plating properties and weldability, and the object of the invention was not achieved.

[0055] Even with steel according to the invention, any problem with any of the treatment conditions fails to satisfy all of the conditions for the retained austenite amount, combination of high strength and press formability, plating properties and weldability, as in the case of samples 65-98, and the object of the invention therefore cannot be achieved.

Table 1

	C	Si	Mn	Al	P	S	N	O	Ni	Cu	B	SiO <sub>2</sub> Bal	D X Cu	Other added elements	Reference
a	0.096	1.42	1.12	0.04	0.014	0.005	0.0032	0.0023	0.61	0.03	-	1.452	-	-	inv. ex.
b	0.12	0.82	1.12	0.06	0.012	0.004	0.0034	0.0022	1.13	0.03	-	0.960	-	-	inv. ex.
c	0.082	1.02	0.82	0.82	0.009	0.003	0.0042	0.0145	2.35	0.04	-	1.676	-	-	inv. ex.
d	0.18	1.45	0.42	0.23	0.021	0.011	0.0120	0.0282	4.2	0.14	-	1.634	-	-	inv. ex.
e	0.06	0.32	2.21	0.12	0.008	0.009	0.0031	0.0023	0.41	0.04	-	0.416	-	-	inv. ex.
f	0.082	0.31	1.02	1.32	0.014	0.005	0.0024	0.0019	1.32	0.03	-	1.366	-	-	inv. ex.
g	0.11	0.92	1.34	0.04	0.011	0.004	0.0034	0.0022	0.42	1.12	-	0.952	-	-	inv. ex.
h	0.092	0.82	0.92	0.13	0.005	0.006	0.0042	0.0052	0.33	0.11	5E-04	0.924	0.00007	-	inv. ex.
i	0.14	1.13	1.04	0.08	0.011	0.014	0.0072	0.0253	0.73	0.34	-	1.194	-	Co:0.00	inv. ex.
j	0.06	0.02	0.52	1.33	0.020	0.031	0.0031	0.0020	3.22	1.23	-	1.084	-	Sn:0.09, Co:0.03	inv. ex.
k	0.12	1.92	0.22	0.03	0.007	0.003	0.0028	0.0017	4.73	1.11	0.008	1.944	0.0021	Mo:0.2	inv. ex.
l	0.14	1.91	0.54	0.03	0.027	0.016	0.0228	0.0031	3.95	1.41	-	1.936	-	Cr:0.8	inv. ex.
m	0.072	0.97	0.59	0.40	0.001	0.013	0.0289	0.0105	0.73	0.93	-	1.293	-	V:0.13	inv. ex.
n	0.16	1.01	2.36	0.71	0.023	0.014	0.0263	0.0119	3.51	0.54	-	1.581	-	Ti:0.03	inv. ex.
o	0.17	1.23	2.20	0.76	0.020	0.008	0.0008	0.0202	1.88	1.14	0.008	1.844	0.00931	Nb:0.04	inv. ex.
p	0.13	1.36	2.13	0.19	0.025	0.001	0.0199	0.0144	1.79	0.78	-	1.513	-	REM(Ce):0.02	inv. ex.
q	0.065	1.92	0.43	0.04	0.004	0.019	0.0260	0.0233	4.15	1.10	-	1.959	-	Ca:0.02	inv. ex.
r	0.17	0.22	0.40	0.42	0.005	0.002	0.0225	0.0167	0.40	0.07	-	0.356	-	Zr:0.03	inv. ex.
s	0.19	0.72	0.74	0.50	0.020	0.002	0.0260	0.0253	1.50	1.31	5E-04	1.116	0.00068	Mg:0.02	inv. ex.
t	0.066	1.58	1.75	0.20	0.023	0.005	0.0016	0.0040	4.63	0.69	-	1.745	-	Zn:0.01	inv. ex.
u	0.11	0.72	2.11	0.75	0.019	0.002	0.0118	0.0167	4.96	0.04	-	1.313	-	W:0.04	inv. ex.
v	0.10	1.43	0.85	0.11	0.024	0.017	0.0252	0.0206	0.74	1.93	-	1.514	-	As:0.01	inv. ex.
w	0.077	1.03	1.20	0.83	0.029	0.004	0.0118	0.0213	3.49	0.56	-	1.692	-	Sn:0.02, Mo:0.32, Ti:0.04	inv. ex.
x	0.084	1.58	0.21	0.09	0.007	0.015	0.0023	0.0021	4.79	1.55	0.003	1.650	0.00419	Cr:0.32, Nb:0.02, Mg:0.02	inv. ex.
y	0.18	1.12	2.17	0.73	0.010	0.001	0.0154	0.0272	3.77	0.48	-	1.707	-	Ti:0.02, Nb:0.03, Ca:0.03, As:0.005	inv. ex.
z	0.12	1.23	0.52	0.12	0.029	0.019	0.0088	0.0251	2.57	0.65	0.007	1.325	0.00465	V:0.22, W:0.01, REM(Y):0.01, Zr:0.02	inv. ex.
ab	0.082	0.37	1.77	0.26	0.027	0.004	0.0024	0.0052	0.96	0.44	-	0.576	-	Mo:0.11, Mg:0.01	inv. ex.
ac	0.12	0.79	0.39	0.92	0.015	0.015	0.0057	0.0145	3.57	0.49	-	1.527	-	Cr:0.42, Ti:0.02, Nb:0.02	inv. ex.
ad	0.03	1.06	1.03	0.55	0.003	0.005	0.0133	0.0034	1.73	0.43	-	1.500	-	-	comp. ex.
ae	0.24	0.89	1.39	0.34	0.006	0.001	0.0023	0.0151	0.65	0.05	-	1.162	-	-	comp. ex.
af	0.13	0.18	1.34	0.39	0.007	0.003	0.0009	0.0203	0.42	1.33	-	0.492	-	-	comp. ex.
ag	0.16	2.11	0.97	0.24	0.008	0.002	0.0110	0.0133	4.76	1.92	8E-04	2.302	0.00153	Sn:0.01, Cr:0.25	comp. ex.
ah	0.15	1.26	0.58	0.001	0.004	0.007	0.0176	0.0202	0.67	1.71	-	1.261	-	-	comp. ex.

Table 1 (cont.)

	Component (weight %)												Reference
	C	Si	Mn	Al	P	S	N	O	Mo	Cr	B	Si:0.8Al	
ai	0.072	0.65	1.52	1.59	0.005	0.003	0.0192	0.0292	4.21	0.71	-	1.922	-
aj	0.10	0.22*	0.85	0.11*	0.024	0.017	0.0252	0.0286	0.75	1.93	-	0.307	-
ak	0.12	1.72*	0.52	0.59*	0.029	0.019	0.0088	0.0251	4.73	0.65	0.007	2.192	Mo:0.04, Ti:0.02
al	0.11	2.12	0.18	0.22	0.008	0.003	0.0133	0.0106	1.84	0.10	-	2.296	-
am	0.14	0.73	2.62	0.54	0.009	0.005	0.0065	0.0269	0.59	0.85	-	1.162	Mo:0.12
an	0.092	1.12	0.69	0.14	0.035	0.007	0.0092	0.0024	0.94	0.05	-	1.232	-
ao	0.12	0.02	1.27	0.22	0.006	0.024	0.0024	0.0042	0.82	1.18	-	0.996	Ca:0.03, Mg:0.02
ap	0.062	1.77	0.02	0.04	0.017	0.017	0.0270	0.0120	0.17	0.02	0.01	1.802	-
aq	0.18	0.23	0.23	0.67	0.004	0.002	0.0087	0.0037	5.23	0.04	-	0.766	Ti:0.04
ar	0.072	1.22	0.02	0.08	0.028	0.007	0.0028	0.0024	0.81	2.17	-	1.284	V:0.21, Zr:0.02

Note: The underlined values in the tables are those outside of the ranges of the invention.

The "\*" marks indicate cases where the relationship between Si and Al was not satisfied.

Table 2

Steel	Heating temperature (°C)	Heating time (min)	Coiling temperature (°C)	Cold rolling draft (%)	Anneal temperature (°C)	Anneal time (sec)	Cooling rate (°C/s)	Pre-plating holding temperature (°C)	Holding time (s)	Plating temperature (°C)	Alloying temperature (°C/s)	Alloying time (s)	Post-plating holding temperature (°C)	Holding time (sec)	Cooling rate (°C/s)	Cooling temperature (°C)
1 a	1250	50	700	70	810	100	10	-	-	440	-	-	-	-	10	180
2 a	1200	60	680	65	800	80	30	400-450	60	450	-	-	-	-	20	180
3 a	1100	80	720	70	760	120	10	400-450	30	430	-	-	350-430	30	10	150
4 a	1230	70	650	70	800	230	15	-	-	450	530	20	-	-	10	200
5 a	1200	60	680	75	820	150	20	400-450	10	460	500	25	-	-	16	150
6 b	1270	50	650	60	660	90	25	-	-	440	480	60	-	-	10	130
7 c	1210	80	660	75	650	50	60	-	-	430	-	-	-	-	8	200
8 d	1160	100	600	50	720	80	150	-	-	470	500	30	-	-	12	180
9 e	1190	80	700	60	770	130	3	360-440	30	460	510	25	-	-	10	210
10 f	1260	55	450	50	820	330	15	-	-	450	-	-	-	-	20	180
11 g	1200	70	700	60	680	130	30	-	-	430	-	-	350-430	30	10	220
12 h	1170	70	600	65	750	60	15	-	-	450	500	30	-	-	15	180
13 i	1190	60	770	70	830	250	8	-	-	440	-	-	-	-	10	150
14 j	1160	80	650	75	700	80	50	-	-	450	480	50	-	-	7	200
15 k	1200	70	700	70	830	30	100	350-400	290	430	500	25	-	-	10	160
16 l	1250	60	600	70	650	60	30	-	-	450	-	-	-	-	20	130
17 m	1220	80	630	68	750	100	10	-	-	460	520	20	-	-	10	200
18 n	1190	90	750	40	800	90	60	400-450	40	440	-	-	-	-	15	180
19 o	1200	60	450	50	770	100	15	-	-	430	550	10	-	-	7	210
20 p	1160	70	620	70	650	30	5	-	-	470	-	-	-	-	10	180
21 q	1260	50	570	60	820	70	100	400-490	15	460	480	40	-	-	12	150
22 r	1190	80	660	75	670	160	30	-	-	450	580	10	-	-	10	200
23 s	1240	70	700	70	760	90	20	-	-	430	500	30	-	-	20	15
24 t	1230	50	480	66	810	280	45	-	-	440	-	-	350-430	30	10	130
25 u	1190	60	620	50	670	160	80	360-440	60	450	-	-	-	-	8	200
26 v	1260	50	550	75	730	30	30	-	-	430	510	25	-	-	20	180
27 w	1270	70	670	45	750	180	20	-	-	450	-	-	-	-	10	210
28 x	1150	90	750	60	820	30	5	-	-	460	500	30	-	-	15	180
29 y	1250	80	580	55	670	150	30	-	-	450	460	60	-	-	10	220
30 z	1210	70	650	40	770	130	70	-	-	460	520	40	-	-	7	180
31 ab	1180	90	660	70	680	220	60	400-450	50	440	-	-	-	-	10	250
32 ac	1200	80	570	75	830	60	20	-	-	430	500	20	-	-	20	180
33 ad	1160	100	600	50	720	80	150	-	-	470	480	30	-	-	10	220
34 ae	1190	80	700	60	770	130	3	-	-	460	-	-	-	-	8	180
35 af	1260	55	450	50	820	330	15	400-450	40	450	540	15	-	-	16	100
36 ag	1200	70	700	60	680	130	30	-	-	430	-	-	-	-	10	150

Table 2 (cont.-1)

Steel	Heating temperature (°C)	Heating time (min)	Coiling temperature (°C)	Cold rolling draft (%)	Anneal temperature (°C)	Anneal time (sec)	Cooling rate (°C/s)	Pre-plating holding temperature (°C)	Holding time (s)	Plating temperature (°C)	Alloying temperature (°C/s)	Alloying time (s)	Post-plating holding temperature (°C)	Holding time (sec)	Cooling rate (°C/s)	Cooling temperature (°C)
37 af	1170	70	600	65	750	60	15	-	-	450	520	20	-	-	8	200
38 af	1190	60	770	70	830	250	8	-	-	440	-	-	-	-	12	170
39 aq	1160	80	850	75	700	80	50	400-450	50	450	500	30	-	-	10	130
40 aq	1200	70	700	70	830	30	100	400-450	50	430	-	-	-	-	20	200
41 ah	1250	60	600	70	650	60	30	-	-	450	480	30	-	-	10	180
42 ah	1220	80	630	68	750	100	10	-	-	460	-	-	350-430	30	15	210
43 ai	1160	100	600	50	720	80	150	-	-	440	550	20	-	-	10	180
44 ai	1190	80	700	60	770	130	3	-	-	430	-	-	-	-	7	270
45 ai	1260	55	450	50	820	330	15	360-440	50	470	580	10	-	-	10	180
46 ai	1200	70	700	60	680	130	30	-	-	460	-	-	-	-	20	250
47 ak	1170	70	600	65	750	60	15	-	-	450	480	60	-	-	10	180
48 ak	1190	60	770	70	830	250	8	-	-	430	-	-	-	-	8	250
49 ai	1160	80	650	75	700	80	50	-	-	440	500	30	-	-	16	180
50 ai	1200	70	700	70	830	30	100	-	-	450	-	-	-	-	10	180
51 am	1250	60	600	70	650	60	30	-	-	430	500	20	-	-	10	220
52 am	1220	80	630	68	750	100	10	400-450	40	450	-	-	350-430	50	12	180
53 an	1190	90	750	40	800	90	60	-	-	460	520	20	-	-	10	250
54 an	1200	60	450	50	770	100	15	-	-	450	-	-	-	-	15	180
55 ao	1160	70	620	70	630	30	5	-	-	460	490	30	-	-	7	220
56 ao	1260	50	570	60	820	70	100	-	-	440	-	-	-	-	10	180
57 ap	1190	80	660	75	670	160	30	360-440	100	430	560	15	-	-	12	180
58 ap	1240	70	700	70	760	90	20	-	-	470	-	-	-	-	10	150
59 aq	1230	50	480	66	810	280	45	-	-	460	500	30	-	-	20	200
60 aq	1190	60	620	50	670	160	80	-	-	450	-	-	350-430	10	10	160
61 ar	1175	90	590	45	790	70	160	-	-	430	480	40	-	-	15	130
62 ar	1200	60	450	50	770	100	15	-	-	450	-	-	-	-	10	200
63 a	1250	50	700	70	810	100	10	-	-	440	-	-	-	-	10	100
64 a	1230	70	550	70	800	230	15	-	-	450	530	20	-	-	8	200
65 a	1140	80	760	60	810	130	70	-	-	430	480	30	-	-	7	180
66 a	1240	40	630	65	680	50	30	-	-	440	550	20	-	-	10	210
67 a	1160	90	380	75	730	90	15	400-450	20	450	500	30	-	-	20	180
68 a	1200	60	790	70	660	220	40	-	-	430	460	60	-	-	10	220
69 a	1280	60	620	30	750	80	60	-	-	450	520	40	-	-	0	100
70 a	1260	80	580	55	630	150	10	-	-	460	500	30	-	-	16	250
71 a	1250	60	720	60	920	50	100	-	-	450	480	40	-	-	10	180
72 a	1160	60	550	75	750	5	6	-	-	430	500	20	-	-	10	250
73 a	1170	70	640	60	680	380	130	-	-	450	550	15	-	-	12	100

Table 2 (cont. -2)

Steel	Heating temperature (°C)	Heating time (min)	Coiling temperature (°C)	Cold rolling draft (%)	Anneal temperature (°C)	Anneal time (sec)	Cooling rate (°C/s)	Pre-plating holding temperature (°C)	Holding time (s)	Plating temperature (°C)	Alloying temperature (°C/s)	Alloying time (s)	Post-plating holding temperature (°C)	Holding time (sec)	Cooling rate (°C/s)	Cooling temperature (°C)
74 a	1160	100	600	50	720	80	1	-	-	460	480	30	-	-	10	170
75 a	1190	80	700	60	770	130	10	300-350	15	440	550	10	-	-	15	100
76 a	1260	55	450	50	820	330	60	480-530	5	430	510	15	-	-	7	220
77 a	1200	70	700	60	680	130	15	360-440	350	470	520	20	-	-	10	180
78 a	1170	70	600	65	750	60	5	-	-	460	430	60	-	-	12	250
79 a	1190	60	770	70	830	250	100	400-450	30	450	520	50	-	-	10	100
80 a	1160	80	650	75	700	80	30	-	-	430	550	5	-	-	10	250
81 a	1200	70	700	70	830	30	20	-	-	440	520	70	-	-	12	180
82 a	1250	60	600	70	650	60	45	-	-	450	500	20	-	-	3	100
83 a	1220	80	630	68	750	100	80	-	-	450	510	20	-	-	15	300
84 a	1140	80	760	60	810	130	160	-	-	430	-	-	-	-	7	150
85 a	1240	40	630	65	680	50	30	-	-	440	-	-	350-430	60	10	200
86 a	1260	90	380	75	730	90	15	400-450	20	450	-	-	-	-	12	180
87 a	1200	60	790	70	660	220	40	-	-	430	-	-	-	-	10	180
88 a	1280	50	620	30	750	80	60	-	-	450	-	-	-	-	18	150
89 a	1260	80	580	55	630	150	10	-	-	460	-	-	350-430	10	10	180
90 a	1250	60	720	60	920	90	100	-	-	450	-	-	-	-	10	180
91 a	1160	60	550	75	750	5	6	-	-	430	-	-	-	-	10	150
92 a	1170	70	640	60	680	380	130	-	-	450	-	-	-	-	20	200
93 a	1190	60	600	65	780	160	1	-	-	460	-	-	-	-	10	170
94 a	1160	60	550	70	670	300	20	300-350	15	440	-	-	350-430	30	12	130
95 a	1200	70	600	80	820	90	60	480-530	5	430	-	-	-	-	10	200
96 a	1160	80	720	60	690	160	5	360-440	400	470	-	-	-	-	15	180
97 a	1190	60	580	65	740	130	3	-	-	440	-	-	-	-	3	210
98 a	1240	80	600	45	690	220	90	-	-	450	-	-	-	-	10	300

Note: The underlined values in the tables are those outside of the ranges of the invention.

The post-plating heating rate was consistently 10 °C/s. The non-alloyed samples are hot-dip zinc-plated steel sheets.

Table 3

	Surface layer Ni (%)	Surface layer Cu (%)	Surface layer Co (%)	Surface layer Sn (%)	Ni+Cu+ (Co+Sn) (%)	Surface layer Si (%)	Surface layer Al (%)	1/4Si + 1/3Al (%)	TS (MPa)	E <sub>1</sub> (%)	Residual $\gamma$ (%)	Reference
1	1.337	0.014	-	-	1.351	2.329	0.425	0.724	625	36	5.5	inv. ex.
2	1.242	0.015	-	-	1.257	2.484	0.628	0.830	611	38	6.3	inv. ex.
3	1.019	0.014	-	-	1.033	2.227	0.506	0.725	609	38	6.5	inv. ex.
4	1.113	0.016	-	-	1.129	2.638	0.694	0.891	631	36	5.4	inv. ex.
5	1.225	0.014	-	-	1.239	2.844	0.535	0.839	624	37	6.3	inv. ex.
6	1.837	0.042	-	-	1.879	2.076	0.144	0.567	645	35	4.9	inv. ex.
7	3.340	0.056	-	-	3.396	2.620	2.219	1.395	589	38	6.5	inv. ex.
8	5.321	0.489	-	-	5.810	3.937	0.571	1.175	716	34	18.5	inv. ex.
9	0.620	0.061	-	-	0.681	0.740	0.273	0.276	612	37	2.8	inv. ex.
10	1.866	0.044	-	-	1.910	0.852	3.442	1.361	563	39	4.5	inv. ex.
11	0.676	1.532	-	-	2.208	2.386	0.091	0.627	613	37	6.3	inv. ex.
12	0.445	0.324	-	-	0.770	2.012	0.347	0.618	590	38	5.5	inv. ex.
13	1.106	0.472	-	0.001	1.579	2.632	0.184	0.719	689	35	10.5	inv. ex.
14	4.925	1.329	0.098	0.123	6.475	1.947	3.156	1.539	616	36	3.2	inv. ex.
15	7.223	1.574	-	-	8.798	4.694	0.072	1.197	705	36	7.5	inv. ex.
16	6.406	2.203	-	-	8.609	4.947	0.079	1.263	756	33	10.3	inv. ex.
17	1.059	1.312	-	-	2.382	2.391	0.999	0.931	603	36	4.3	inv. ex.
18	4.956	0.809	-	-	5.764	2.428	1.807	1.209	805	35	13.5	inv. ex.
19	2.790	1.843	-	-	4.633	2.887	1.722	1.296	830	32	15.5	inv. ex.
20	1.985	1.095	-	-	3.080	3.222	0.422	0.945	680	35	8.3	inv. ex.
21	5.718	1.641	-	-	7.359	4.495	0.111	1.161	615	38	3.5	inv. ex.
22	0.543	0.105	-	-	0.647	0.546	1.097	0.502	604	36	14.5	inv. ex.
23	2.312	1.982	-	-	4.294	1.825	1.163	0.844	720	34	18.9	inv. ex.

Table 3 (continued)

	Surface layer Ni (%)	Surface layer Cu (%)	Surface layer Co (%)	Surface layer Sn (%)	Ni+Cu+ (Co+Sn) (%)	Surface layer Si (%)	Surface layer Al (%)	1/4Si + 1/3Al (%)	TS (MPa)	E1 (%)	Residual $\gamma$ (%)	Reference
24	7.288	1.039	-	-	8.328	4.349	0.499	1.254	630	38	4.5	inv. ex.
25	7.230	0.049	-	-	7.279	1.873	1.799	1.068	635	39	8.5	inv. ex.
26	1.087	2.823	-	-	3.911	3.701	0.263	1.013	640	36	6.3	inv. ex.
27	5.310	0.858	-	0.025	6.193	2.309	2.242	1.325	720	33	3.8	inv. ex.
28	7.311	2.390	-	-	9.701	4.247	0.210	1.132	710	33	4.5	inv. ex.
29	6.042	0.776	-	-	6.818	2.843	2.002	1.378	830	32	17.5	inv. ex.
30	3.483	0.927	-	-	4.410	2.979	0.291	0.842	620	36	8.3	inv. ex.
31	1.519	0.668	-	-	2.187	0.903	0.668	0.449	590	40	5.2	inv. ex.
32	5.172	0.798	-	-	5.970	2.043	2.201	1.244	624	37	7.5	inv. ex.
33	2.468	0.486	-	-	2.954	2.400	1.240	1.014	498	34	1.5	comp. ex.
34	2.625	0.596	-	-	3.221	2.389	1.327	1.040	504	35	1.3	comp. ex.
35	1.020	0.070	-	-	1.090	2.225	0.792	0.820	892	33	22.5	comp. ex.
36	0.925	0.069	-	-	0.994	2.325	0.932	0.892	904	31	23	comp. ex.
37	0.583	2.063	-	-	2.645	0.435	0.910	0.412	612	30	1.5	comp. ex.
38	0.625	2.156	-	-	2.781	0.416	0.892	0.401	604	29	1.8	comp. ex.
39	5.569	2.648	0.000	0.017	8.234	5.059	0.428	1.407	710	35	13.3	comp. ex.
40	6.534	3.142	0.003	0.010	9.689	5.539	0.546	1.567	720	36	14.2	comp. ex.
41	0.990	2.809	-	-	3.800	3.338	0.002	0.835	612	30	1.5	comp. ex.
42	0.980	2.715	-	-	3.695	3.459	0.004	0.866	605	32	1.8	comp. ex.
43	5.727	1.053	-	-	6.780	1.551	4.125	1.763	605	36	4.3	comp. ex.
44	6.146	1.214	-	-	7.360	1.429	3.958	1.677	600	37	4.5	comp. ex.
45	1.017	3.065	-	-	4.082	0.586	0.287	0.242	580	36	1.4	comp. ex.
46	0.814	2.562	-	-	3.376	0.954	0.359	0.358	590	34	1.3	comp. ex.
47	7.510	1.010	-	-	8.519	4.895	1.837	1.836	710	34	6.8	comp. ex.



Table 3 (continued)

	Surface layer Ni (%)	Surface layer Cu (%)	Surface layer Co (%)	Surface layer Sn (%)	Ni+Cu+ (Co+Sn) (%)	Surface layer Si (%)	Surface layer Al (%)	1/4Si + 1/3Al (%)	TS (MPa)	E1 (%)	Residual $\gamma$ (%)	Reference
48	8.015	1.136	-	-	9.151	4.526	1.624	1.673	705	33	7.5	comp.ex.
49	2.959	0.134	-	-	3.102	5.039	0.554	1.445	590	34	1.3	comp.ex.
50	3.015	0.193	-	-	3.208	4.689	0.456	1.324	585	33	1.8	comp.ex.
51	0.820	1.363	-	-	2.183	1.717	1.403	0.897	730	33	9.5	comp.ex.
52	0.725	1.236	-	-	1.961	2.016	1.826	1.113	725	34	10.3	comp.ex.
53	1.289	0.069	-	-	1.358	2.601	0.358	0.770	630	35	6.3	comp.ex.
54	1.302	0.102	-	-	1.404	2.506	0.334	0.738	635	34	5.3	comp.ex.
55	1.113	1.676	-	-	2.789	1.891	0.550	0.656	640	34	8.2	comp.ex.
56	1.325	1.893	-	-	3.218	1.793	0.490	0.612	630	35	7.9	comp.ex.
57	0.261	0.027	-	-	0.288	4.415	0.104	1.138	590	37	4.3	comp.ex.
58	0.325	0.035	-	-	0.360	4.036	0.089	1.039	500	36	3.8	comp.ex.
59	7.325	0.061	-	-	7.386	0.590	1.755	0.732	780	18	21.5	comp.ex.
60	6.801	0.063	-	-	6.864	0.756	2.026	0.864	790	15	23.5	comp.ex.
61	1.116	3.253	-	-	4.369	3.312	0.187	0.890	620	26	3.8	comp.ex.*
62	1.236	3.456	-	-	4.692	3.016	0.159	0.807	625	27	2.7	comp.ex.*
63	1.337	0.014	-	-	1.351	2.329	0.425	0.724	525	36	5.5	comp.ex.
64	1.113	0.016	-	-	1.129	2.638	0.694	0.891	631	36	5.4	comp.ex.
65	0.826	0.003	-	-	0.829	3.345	0.863	1.124	640	35	5.5	comp.ex.
66	0.816	0.004	-	-	0.820	3.015	0.726	0.996	620	35	6.3	comp.ex.
67	0.861	0.012	-	-	0.873	3.012	0.786	1.015	630	34	5.3	comp.ex.
68	1.325	0.045	-	-	1.370	2.756	0.426	0.831	625	34	3.5	comp.ex.**
69	1.426	0.068	-	-	1.494	2.726	0.531	0.859	610	29	0.6	comp.ex.
70	1.324	0.016	-	-	1.340	2.627	0.426	0.799	650	26	1.8	comp.ex.
71	1.236	0.013	-	-	1.249	3.456	0.597	1.063	580	30	1.5	comp.ex.

Table 3 (continued)

	Surface layer Ni (%)	Surface layer Cu (%)	Surface layer Co (%)	Surface layer Sn (%)	Ni+Cu+ (Co+Sn) (%)	Surface layer si (%)	Surface layer Al (%)	1/4Si + 1/3Al (%)	TS (MPa)	E1 (%)	Residual $\gamma$ (%)	Reference
72	1.013	0.009	-	-	1.022	3.015	0.624	0.962	630	29	1.2	comp.ex.
73	1.106	0.012	-	-	1.118	2.984	0.601	0.946	635	28	1	comp.ex.
74	1.068	0.010	-	-	1.078	3.126	0.726	1.024	640	26	0	comp.ex.
75	1.215	0.015	-	-	1.230	2.957	0.543	0.920	645	27	1.2	comp.ex.
76	1.456	0.025	-	-	1.481	2.745	0.459	0.839	630	25	0	comp.ex.
77	1.235	0.014	-	-	1.249	2.924	0.585	0.926	635	26	0.5	comp.ex.
78	1.126	0.010	-	-	1.136	2.957	0.624	0.947	630	36	5.3	comp.ex.
79	1.198	0.011	-	-	1.209	2.843	0.546	0.893	625	25	0.3	comp.ex.
80	1.016	0.006	-	-	1.022	3.146	0.657	1.006	630	30	1.6	comp.ex.
81	1.267	0.009	-	-	1.276	2.782	0.495	0.861	620	26	0.8	comp.ex.
82	1.395	0.023	-	-	1.418	2.568	0.406	0.777	620	26	0.5	comp.ex.
83	1.304	0.019	-	-	1.323	2.654	0.416	0.802	630	28	1.1	comp.ex.
84	0.804	0.008	-	-	0.812	3.159	0.789	1.053	645	34	5.3	comp.ex.
85	0.812	0.009	-	-	- 0.821	3.015	0.756	1.006	622	35	6.5	comp.ex.
86	0.834	0.011	-	-	0.845	3.214	0.658	1.023	635	33	5.5	comp.ex.
87	1.325	0.015	-	-	1.340	2.795	0.498	0.865	620	33	3.3	comp.ex.**
88	1.426	0.016	-	-	1.442	2.846	0.501	0.879	615	28	0.7	comp.ex.
89	1.325	0.015	-	-	1.340	2.783	0.504	0.864	645	26	1.3	comp.ex.
90	1.359	0.017	-	-	1.376	3.214	0.785	1.065	575	28	1.6	comp.ex.
91	1.015	0.010	-	-	1.025	3.012	0.688	0.982	625	27	1.1	comp.ex.
92	1.105	0.010	-	-	1.115	2.986	0.657	0.966	640	26	0.8	comp.ex.
93	1.168	0.008	-	-	1.176	2.904	0.604	0.927	635	25	0	comp.ex.
94	1.015	0.009	-	-	1.024	2.954	0.715	0.977	640	26	1.1	comp.ex.
95	1.235	0.015	-	-	1.250	2.716	0.546	0.861	635	26	0	comp.ex.

Table 3 (continued)

	Surface Ni layer (%)	Surface Cu layer (%)	Surface Co layer (%)	Surface Sn layer (%)	Ni+Cu+ (Co+Sn) (%)	Surface layer Si (%)	Surface layer Al (%)	1/4Si + 1/3Al (%)	TS (MPa)	E1 (%)	Residual $\gamma$ (%)	Reference
96	1.015	0.010	-	-	1.025	2.957	0.750	0.989	630	25	0.5	comp. ex.
97	1.126	0.011	-	-	1.137	3.015	0.657	0.973	625	24	0.7	comp. ex.
98	1.348	0.013	-	-	1.361	2.647	0.459	0.815	635	27	0.9	comp. ex.
Note: The underlined values in the tables are those outside of the ranges of the invention. The "comp. ex." references indicate samples with poor strength/ductility balance that did not achieve the object of the invention. The "comp. ex. ***" references indicate samples that had residual oxides due to insufficient acid washing after rolling, and thus had impaired plating adhesion. The samples with Sn and Co indicated by "-" are those where the steel contained no Sn or Co, and those elements were therefore not measured.												

Table 4

	Components in plating layer (%) (remainder: Zn and unavoidable impurities)										Weldability	Plating property	Plating adhesion	Reference
	Fe	Al	Mn	Pb	Sb	Ni	Cu	Co	Sn	Cd	Cr			
1	0.08	0.24	0.004	0.002	0.006	0.168	0.001	0.002	0.010	0.004	0.034	○	⊙	inv. ex.
2	0.06	0.64	0.009	0.003	0.006	0.340	0.003	0.002	0.000	0.003	0.025	○	⊙	inv. ex.
3	0.11	0.19	0.003	0.002	0.007	0.223	0.004	0.004	0.002	0.005	0.011	○	⊙	inv. ex.
4	11.5	0.24	0.013	0.006	0.000	0.272	0.004	0.002	0.009	0.002	0.034	○	⊙	inv. ex.
5	10.8	0.26	0.007	0.008	0.003	0.222	0.005	0.011	0.008	0.003	0.039	○	⊙	inv. ex.
6	9.6	0.26	0.006	0.004	0.002	0.133	0.009	0.012	0.005	0.000	0.007	○	⊙	inv. ex.
7	0.07	0.33	0.008	0.000	0.003	0.114	0.003	0.003	0.002	0.008	0.026	○	⊙	inv. ex.
8	8.6	0.28	0.015	0.006	0.007	2.017	0.175	0.003	0.009	0.003	0.013	○	⊙	inv. ex.
9	9.2	0.27	0.005	0.002	0.003	0.191	0.001	0.003	0.001	0.000	0.029	○	⊙	inv. ex.
10	0.03	0.21	0.006	0.000	0.007	0.236	0.017	0.002	0.000	0.002	0.013	○	⊙	inv. ex.
11	0.05	0.22	0.001	0.003	0.005	0.045	0.045	0.011	0.007	0.001	0.017	○	⊙	inv. ex.
12	10.2	0.21	0.009	0.001	0.006	0.169	0.059	0.008	0.004	0.007	0.023	○	⊙	inv. ex.
13	0.06	0.30	0.005	0.003	0.001	0.203	0.138	0.006	0.008	0.005	0.015	○	⊙	inv. ex.
14	9.6	0.32	0.005	0.002	0.006	1.569	0.637	0.013	0.035	0.007	0.036	○	⊙	inv. ex.
15	10.2	0.30	0.003	0.006	0.002	2.273	0.659	0.008	0.005	0.004	0.018	○	⊙	inv. ex.
16	0.05	0.26	0.001	0.004	0.003	1.912	0.878	0.003	0.010	0.008	0.037	○	⊙	inv. ex.
17	10.1	0.34	0.007	0.008	0.003	0.307	0.488	0.011	0.002	0.008	0.031	○	⊙	inv. ex.
18	0.09	0.26	0.011	0.007	0.007	0.064	0.254	0.001	0.002	0.001	0.001	○	⊙	inv. ex.
19	11.5	0.28	0.006	0.004	0.004	0.311	0.350	0.005	0.011	0.004	0.020	○	⊙	inv. ex.
20	0.16	0.73	0.007	0.006	0.008	0.607	0.193	0.001	0.003	0.005	0.026	○	⊙	inv. ex.
21	8.6	0.19	0.016	0.004	0.005	0.512	0.260	0.007	0.006	0.005	0.020	○	⊙	inv. ex.
22	11.3	0.30	0.005	0.006	0.002	0.159	0.008	0.012	0.004	0.005	0.002	○	○	inv. ex.
23	10.5	0.24	0.017	0.006	0.003	0.820	0.826	0.006	0.010	0.004	0.000	○	⊙	inv. ex.

Table 4 (continued)

	Components in plating layer (%) (remainder: Zn and unavoidable impurities)										Weldability	Plating property	Plating adhesion	Reference
	Fe	Al	Mn	Pb	Sb	Ni	Cu	Co	Sn	Cd	Cr			
24	0.03	0.21	0.006	0.006	0.006	0.378	0.035	0.007	0.003	0.007	0.021	○	⊙	inv. ex.
25	0.05	0.23	0.007	0.004	0.004	2.835	0.009	0.005	0.001	0.006	0.008	○	⊙	inv. ex.
26	9.8	0.26	0.011	0.007	0.002	0.314	0.907	0.006	0.010	0.007	0.033	○	⊙	inv. ex.
27	0.11	0.30	0.008	0.006	0.001	2.070	0.208	0.005	0.015	0.004	0.025	○	⊙	inv. ex.
28	10.2	0.29	0.001	0.001	0.004	1.924	0.266	0.009	0.010	0.003	0.022	○	⊙	inv. ex.
29	8.6	0.27	0.009	0.004	0.006	0.963	0.167	0.011	0.006	0.006	0.037	○	⊙	inv. ex.
30	11.3	0.34	0.005	0.006	0.003	0.582	0.054	0.003	0.000	0.004	0.002	○	⊙	inv. ex.
31	0.04	0.20	0.011	0.000	0.002	0.412	0.107	0.011	0.003	0.001	0.015	○	⊙	inv. ex.
32	9.8	0.18	0.009	0.005	0.005	1.437	0.216	0.010	0.004	0.004	0.021	○	⊙	inv. ex.
33	8.6	0.31	0.001	0.003	0.004	0.143	0.044	0.011	0.010	0.001	0.035	○	⊙	comp. ex.
34	0.13	0.26	0.006	0.002	0.004	0.015	0.116	0.002	0.005	0.006	0.015	○	⊙	comp. ex.
35	10.8	0.19	0.007	0.000	0.008	0.179	0.003	0.003	0.001	0.002	0.034	○	○	comp. ex.
36	0.06	0.28	0.017	0.006	0.000	0.026	0.011	0.011	0.003	0.000	0.007	○	○	comp. ex.
37	12.3	0.27	0.007	0.000	0.007	0.154	0.376	0.000	0.004	0.008	0.012	○	⊙	comp. ex.
38	0.01	0.31	0.015	0.001	0.002	0.013	0.091	0.006	0.003	0.000	0.003	○	⊙	comp. ex.
39	10.5	0.34	0.009	0.007	0.004	0.692	0.738	0.007	0.012	0.001	0.007	○	○	comp. ex.
40	0.11	0.28	0.002	0.005	0.003	1.716	0.658	0.007	0.010	0.007	0.022	○	○	comp. ex.
41	8.6	0.28	0.006	0.004	0.007	0.242	0.382	0.006	0.011	0.000	0.039	○	⊙	comp. ex.
42	0.1	0.29	0.017	0.004	0.003	0.125	0.754	0.006	0.003	0.000	0.038	○	⊙	comp. ex.
43	11.3	0.35	0.011	0.007	0.008	1.013	0.197	0.004	0.009	0.004	0.011	○	○	comp. ex.
44	0.06	0.20	0.006	0.002	0.006	0.134	0.002	0.005	0.008	0.001	0.022	○	○	comp. ex.
45	13.3	0.24	0.011	0.005	0.007	0.008	0.718	0.012	0.012	0.008	0.029	○	⊙	comp. ex.
46	0.05	0.21	0.000	0.007	0.005	0.015	0.089	0.008	0.009	0.008	0.003	○	⊙	comp. ex.

Table 4 (continued)

	Components in plating layer (%) (remainder: Zn and unavoidable impurities)										Weldability	Plating property	Plating adhesion	Reference
	Fe	Al	Mn	Pb	Sb	Ni	Cu	Co	Sn	Cd	Cr			
47	8.9	0.84	0.009	0.003	0.008	1.118	0.237	0.003	0.005	0.001	0.033	○	.	comp. ex.
48	0.1	0.23	0.010	0.002	0.006	0.626	0.029	0.002	0.005	0.007	0.038	○	.	comp. ex.
49	11.3	0.20	0.001	0.006	0.007	0.428	0.034	0.004	0.007	0.001	0.022	○	⊙	comp. ex.
50	0.01	0.26	0.003	0.007	0.007	0.865	0.045	0.010	0.007	0.005	0.004	○	⊙	comp. ex.
51	10.5	0.20	0.007	0.004	0.003	0.151	0.055	0.007	0.006	0.002	0.012	Δ	⊙	comp. ex.
52	0.04	0.20	0.009	0.006	0.001	0.025	0.181	0.000	0.008	0.005	0.017	Δ	⊙	comp. ex.
53	12.2	0.30	0.018	0.008	0.001	0.168	0.016	0.005	0.002	0.002	0.011	Δ	⊙	comp. ex.
54	0.07	0.22	0.013	0.000	0.005	0.171	0.002	0.002	0.004	0.001	0.015	Δ	⊙	comp. ex.
55	10.8	0.26	0.013	0.006	0.002	0.283	0.452	0.009	0.005	0.002	0.004	.	⊙	comp. ex.
56	0.06	0.35	0.016	0.001	0.002	0.090	0.432	0.004	0.009	0.002	0.032	.	⊙	comp. ex.
57	13.5	0.23	0.012	0.004	0.005	0.047	0.002	0.011	0.007	0.005	0.037	○	.	comp. ex.
58	0.14	0.27	0.012	0.004	0.001	0.052	0.001	0.001	0.008	0.006	0.036	○	.	comp. ex.
59	10.3	0.27	0.001	0.004	0.001	0.237	0.015	0.009	0.009	0.005	0.039	○	⊙	comp. ex.
60	0.04	0.28	0.016	0.006	0.002	0.479	0.007	0.010	0.005	0.001	0.038	○	⊙	comp. ex.
61	10.5	0.27	0.015	0.004	0.006	0.239	0.595	0.009	0.001	0.003	0.011	○	⊙	comp. ex.*
62	0.12	0.30	0.002	0.001	0.004	0.297	0.385	0.011	0.002	0.005	0.021	○	⊙	comp. ex.*
63	0.08	1.35	0.004	0.002	0.006	0.168	0.001	0.002	0.010	0.004	0.034	○	⊙	comp. ex.
64	11.5	1.26	0.013	0.006	0.000	0.272	0.004	0.002	0.009	0.002	0.034	○	⊙	comp. ex.
65	9.2	0.32	0.009	0.005	0.001	0.013	0.000	0.005	0.008	0.003	0.003	○	.	comp. ex.
66	13.5	0.19	0.012	0.001	0.006	0.196	0.000	0.005	0.004	0.004	0.036	○	.	comp. ex.
67	10.5	0.30	0.000	0.006	0.006	0.065	0.001	0.002	0.000	0.005	0.008	○	.	comp. ex.
68	9.6	0.33	0.003	0.003	0.001	0.316	0.000	0.010	0.008	0.001	0.032	○	Δ	comp. ex.**
69	12.2	0.19	0.008	0.003	0.006	0.324	0.015	0.012	0.003	0.003	0.026	○	⊙	comp. ex.

Table 4 (continued)

	Components in plating layer (%) (remainder: Zn and unavoidable impurities)										Weldability	Plating property	Plating adhesion	Reference
	Fe	Al	Mn	Pb	Sb	Ni	Cu	Co	Sn	Cd	Cr			
70	10.5	0.20	0.003	0.004	0.005	0.261	0.001	0.009	0.004	0.003	0.029	⊙	⊙	comp. ex.
71	9.1	0.20	0.004	0.000	0.002	0.205	0.004	0.004	0.012	0.006	0.028	○	○	comp. ex.
72	10.1	0.26	0.018	0.004	0.007	0.282	0.001	0.009	0.006	0.002	0.031	○	○	comp. ex.
73	13.2	0.30	0.004	0.003	0.008	0.084	0.002	0.008	0.000	0.002	0.005	○	⊙	comp. ex.
74	8.34	0.93	0.015	0.005	0.006	0.077	0.001	0.011	0.002	0.003	0.005	○	○	comp. ex.
75	12.5	0.32	0.004	0.005	0.006	0.243	0.001	0.003	0.008	0.005	0.002	⊙	⊙	comp. ex.
76	10.3	0.18	0.012	0.006	0.004	0.355	0.002	0.004	0.011	0.001	0.009	○	⊙	comp. ex.
77	12.1	0.25	0.014	0.001	0.001	0.339	0.003	0.007	0.001	0.007	0.008	○	⊙	comp. ex.
78	5.3	0.33	0.005	0.006	0.007	0.197	0.000	0.012	0.011	0.007	0.000	○	○	comp. ex.
79	16.5	0.33	0.011	0.005	0.004	0.052	0.000	0.000	0.008	0.004	0.032	○	⊙	comp. ex.
80	5.1	0.24	0.008	0.004	0.007	0.183	0.000	0.007	0.009	0.002	0.013	○	○	comp. ex.
81	15.6	0.28	0.012	0.006	0.004	0.042	0.001	0.009	0.008	0.003	0.006	○	⊙	comp. ex.
82	9.8	0.30	0.008	0.007	0.003	0.165	0.005	0.003	0.008	0.005	0.029	○	⊙	comp. ex.
83	10.5	0.30	0.013	0.004	0.005	0.269	0.004	0.001	0.005	0.004	0.032	○	⊙	comp. ex.
84	0.04	0.34	0.015	0.000	0.008	0.106	0.001	0.000	0.003	0.008	0.000	○	·	comp. ex.
85	0.16	0.25	0.012	0.007	0.004	0.218	0.002	0.001	0.011	0.005	0.001	○	·	comp. ex.
86	0.04	0.20	0.004	0.006	0.006	0.052	0.002	0.004	0.005	0.006	0.028	○	·	comp. ex.
87	0.07	0.30	0.014	0.007	0.002	0.380	0.001	0.000	0.006	0.004	0.013	○	Δ	comp. ex.**
88	0.1	0.23	0.011	0.004	0.007	0.353	0.000	0.002	0.009	0.008	0.026	○	⊙	comp. ex.
89	0.13	0.29	0.009	0.008	0.006	0.394	0.001	0.006	0.007	0.004	0.016	○	⊙	comp. ex.
90	0.16	0.32	0.017	0.006	0.007	0.331	0.001	0.011	0.001	0.006	0.017	○	⊙	comp. ex.
91	0.16	0.64	0.014	0.007	0.002	0.300	0.001	0.009	0.008	0.000	0.019	○	○	comp. ex.
92	0.04	0.27	0.008	0.002	0.001	0.117	0.002	0.007	0.005	0.000	0.024	○	⊙	comp. ex.
93	0.16	0.22	0.08	0.003	0.007	0.242	0.002	0.011	0.004	0.007	0.002	○	⊙	comp. ex.

Table 4 (continued)

	Components in plating layer (%) (remainder: Zn and unavoidable impurities)										Weldability	Plating property	Plating adhesion	Reference
	Fe	Al	Mn	Pb	Sb	Ni	Cu	Co	Sn	Cd	Cr			
94	0.06	0.25	0.05	0.004	0.002	0.028	0.000	0.005	0.002	0.000	0.003	○	○	comp. ex.
95	0.13	0.22	0.015	0.004	0.001	0.264	0.003	0.012	0.007	0.001	0.005	○	⊙	comp. ex.
96	0.09	0.30	0.007	0.007	0.004	0.168	0.001	0.005	0.011	0.002	0.014	○	○	comp. ex.
97	0.11	0.31	0.010	0.001	0.003	0.307	0.003	0.011	0.007	0.008	0.001	○	⊙	comp. ex.
98	0.01	0.30	0.05	0.003	0.005	0.292	0.002	0.009	0.005	0.002	0.017	○	⊙	comp. ex.
Note: The underlined values in the tables are those outside of the ranges of the invention. The "comp. ex." references indicate samples with poor strength/ductility balance that did not achieve the object of the invention. The "comp. ex. **" references indicate samples that had residual oxides due to insufficient acid washing after rolling, and thus had impaired plating adhesion. The samples with Sn and Co indicated by "-" are those where the steel contained no Sn or Co, and those elements were therefore not measured.														



Industrial Applicability

[0056] As explained above, according to the present invention there are provided high strength hot-dip galvanized and galvanized steel sheets with satisfactory press formability and plating adhesion, as well as a process for efficient manufacture of the steel sheets.

**Claims**

1. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, the steel sheet containing in terms of weight percent,

C: 0.05-0.2%,  
Si: 0.2-2.0%,  
Mn: 0.2-2.5%,  
Al: 0.01-1.5%,  
Ni: 0.2-5.0%,  
P: <0.03% and  
S: <0.02%

where the relationship between Si and Al is such that  $0.4(\%) \leq \text{Si} + 0.8 \text{ Al}(\%) \leq 2.0\%$  and the remainder consists of Fe and unavoidable impurities, **characterized in that** the volume percentage of the retained austenite in the steel sheet is 2-20% and the steel sheet surface wherein the relationship between the Ni and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn plating layer comprising Al:  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

2. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized by** also containing, in addition to the steel sheet components mentioned in claim 1 in terms of weight percent, Cu at less than 2.0%, wherein the volume percentage of the retained austenite in the steel sheet is 2-20%, and the relationship between the Ni, Cu and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ .

3. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized by** also containing, in addition to the steel sheet components mentioned in claim 2, in terms of weight percent, B at 0.0002-0.01%, wherein the relationship of Cu and B is such that  $\text{B} \times \text{Cu}(\%) \geq 0.00005(\%)$ .

4. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized by** also containing, in addition to the steel sheet components mentioned in any of claims 1 to 3, in terms of weight percent, at least one from among Co at <0.3% and Sn at <0.3%, wherein the volume percentage of the retained austenite in the steel sheet is 2-20% and the relationship between the Ni, Cu, Co, Sn and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu} + \text{Co} + \text{Sn}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ .

5. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized by** also containing in addition to the steel sheet components mentioned in any of claims 1 to 4, at least one from among Mo: <0.5%, Cr: <1%, V: <0.3%, Ti: <0.06%, Nb: <0.06%, REM: <0.05%, Ca: <0.05%, Zr: <0.05%, Mg: <0.05%, Zn: <0.02%, W: <0.05%, As: <0.02%, N: <0.03% and O: <0.05%.

6. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized in that** the steel sheet surface of any of claims 1 to 5 has a Zn plating layer containing at least one from among Al:  $\leq 1\%$ , Mn: <0.02%, Pb: <0.01%, Fe: <0.2%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with the remainder Zn and unavoidable impurities.

7. A high strength alloyed hot-dip galvanized steel sheet with excellent press formability, **characterized in that** a steel sheet containing in terms of weight percent,

C: 0.05-0.2%,  
Si: 0.2-2.0%,  
Mn: 0.2-2.5%,

Al: 0.01-1.5%,  
 Ni: 0.2-5.0%,  
 P: <0.03% and  
 S: <0.02%,

where the relationship between Si and Al is such that  $0.4(\%) \leq \text{Si} + 0.8 \text{ Al}(\%) \leq 2.0\%$ , the remainder consists of Fe and unavoidable impurities, the volume percentage of said retained austenite in the steel sheet is 2-20% and the relationship between the Ni and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe: 8-15%, Al:  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

8. A high strength hot-dip galvanized steel sheet with excellent press formability, **characterized in that** a steel sheet also containing, in addition to the steel sheet components mentioned in claim 7, in terms of weight percent, Cu at less than 2.0% with the remainder Fe and unavoidable impurities, wherein the volume percentage of the retained austenite in said steel sheet is 2-20%, and the relationship between the Ni, Cu and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

9. A high strength hot-dip galvanized steel sheet with excellent press formability, **characterized in that** a steel sheet also containing, in addition to the steel sheet components mentioned in claim 7, in terms of weight percent, B at 0.0002-0.01% where the relationship between Cu and B is such that  $\text{B} \times \text{Cu}(\%) \geq 0.00005(\%)$  with the remainder Fe and unavoidable impurities, has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

10. A high strength hot-dip galvanized steel sheet with excellent press formability, **characterized in that** a steel sheet containing, in addition to the steel sheet components mentioned in any of claims 7 to 9, in terms of weight percent, at least one from among Co at <0.3% and Sn at  $\leq 0.3\%$  with the remainder Fe and unavoidable impurities, wherein the volume percentage of the retained austenite in said steel sheet is 2-20% and the relationship between the Ni, Cu, Co, Sn and Si, Al in 0.5  $\mu\text{m}$  of the steel sheet surface layer is such that  $\text{Ni} + \text{Cu} + \text{Co} + \text{Sn}(\%) \geq 1/4 \text{ Si} + 1/3 \text{ Al}(\%)$ , has a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities.

11. A high strength hot-dip galvanized steel sheet with excellent press formability, **characterized by** also containing, in addition to the steel sheet components mentioned in any of claims 7 to 10, at least one from among Mo: <0.5%, Cr: <1%, V: <0.3%, Ti: <0.06%, Nb: <0.06%, REM: <0.05%, Ca: <0.05%, Zr: <0.05%, Mg: <0.05%, Zn: <0.02%, W: <0.05%, As: <0.02%, N: <0.03% and O: <0.05%.

12. A high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability, **characterized in that** the steel sheet surface of any of claims 7 to 11 has a Zn plating layer containing at least one from among Fe: 8-15%, Al:  $\leq 1\%$ , Mn: <0.02%, Pb: <0.01%, Sb: <0.01%, Ni: <3.0%, Cu: <1.5%, Sn: <0.1%, Co: <0.1%, Cd: <0.01% and Cr: <0.05%, with the remainder Zn and unavoidable impurities.

13. A process for the manufacture of a high strength hot-dip galvanized steel sheet with excellent plating adhesion and press formability **characterized by** having 2-20% retained austenite and a Zn plating layer comprising Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities, whereby a steel sheet having the component composition of any one of claims 1 to 6 is cast and solidified and then heated at 1150° or higher for at least 45 minutes, after which it is subjected to hot rolling and coiling at 400-780°C, and then after descaling treatment is subjected to cold rolling at a reduction ratio of 35-85%, subsequently annealed from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C, and finally cooled to 350-500 °C at a cooling rate of 2-200 °C/s, subjected to hot-dip galvanizing and then cooled to below 250°C at a cooling rate of at least 5 °C/s.

14. A process for the manufacture of a high strength hot-dip galvanized steel sheet with excellent press formability **characterized by** having 2-20% retained austenite and a Zn alloy plating layer comprising Fe at 8-15% and Al at  $\leq 1\%$  with the remainder Zn and unavoidable impurities, whereby a steel sheet having the component composition of any one of claims 7 to 12 is cast and solidified and then heated at 1150°C or higher for at least 45 minutes, after which it is subjected to hot rolling and coiling at 400-780°C, and then after descaling treatment is subjected to cold rolling at a reduction ratio of 35-85%, subsequently annealed from 10 seconds to 6 minutes in the two-phase temperature range of 650-900 °C, and finally cooled to 350-500 °C at a cooling rate of 2-200 °C/s, subjected to

## EP 1 160 346 A1

hot-dip galvanizing and then held in a temperature range of 450-600°C for 5 seconds to 1 minute prior to cooling to below 250°C at a cooling rate of at least 5 °C/s.

- 5      **15.** A process for the manufacture of a high strength hot-dip galvanized steel sheet with excellent press formability according to claim 13 or 14, **characterized in that** said cold rolling is followed by annealing from 10 seconds to 6 minutes in the two-phase temperature range of 650-900°C and then by cooling to 350-500°C at a cooling rate of 2-200 °C/s and held **in that** temperature range for no more than 5 minutes.

10

15

20

25

30

35


40

45

50

55

Fig.1



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP99/06774

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> C17 C22C 38/00, 38/06, 38/58, C21D 9/46		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) C17 C22C 38/00-38/58, C21D 9/46		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1926-1996 Toroku Jitsuyo Shinan Koho 1994-2000 Kokai Jitsuyo Shinan Koho 1971-2000 Jitsuyo Shinan Toroku Koho 1996-2000		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 5-247586, A (NKK CORPORATION), 24 September, 1993 (24.09.93) (Family: none)	1-15
A	JP, 9-13147, A (Nippon Steel Corporation), 14 January, 1997 (14.01.97) (Family: none)	1-15
A	JP, 8-199288, A (Kobe Steel, Ltd.), 06 August, 1996 (06.08.96) (Family: none)	1-15
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed		"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "Δ" document member of the same patent family
Date of the actual completion of the international search 28 February, 2000 (28.02.00)		Date of mailing of the international search report 07.03.00
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ ~~FADED TEXT OR DRAWING~~
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**